

A Contemporary Assessment on Composite Titania onto Graphitic Carbon Nitride-Based Catalyst as Photocatalyst

Azami M. S.¹, Jalil A. A.^{2,3,*}, Hitam C. N. C.^{2,3}, Mamat C. R.¹, Siang T. J.², Hussain I.¹, Hambali H. U.²

¹Department of Chemistry, Faculty of Science, Universiti Teknologi Malaysia, 81310 UTM Johor Bahru, Johor, Malaysia

²School of Chemical and Energy Engineering, Faculty of Engineering, Universiti Teknologi Malaysia, 81310 UTM Johor Bahru, Johor, Malaysia

³Centre of Hydrogen Energy, Institute of Future Energy, Universiti Teknologi Malaysia, 81310 UTM Johor Bahru, Johor, Malaysia

*Corresponding author: aishahaj@utm.my

Article History

Received: July 22, 2018

Received in revised form: January 20, 2019

Accepted: May 23, 2019

Published Online: June 24, 2019

Abstract

Titanium dioxide (TiO₂) has drawn widespread interest by researchers as a precious semiconductor that is responsive towards photodegradation of various pollutants. This catalyst has its own limitations such as fast electron-hole recombination, wide band gap, and can only be utilised under ultraviolet (UV) region. In order to overcome these problems, the addition of a metal-free dopant is a common practice to prevent electron-hole recombination and enhance photodegradation under visible light. Among various types of metal-free catalysts, carbon nitride material has received much attention due to its numerous benefits such as good in terms of physical and chemical strength, as well as an attractive electronic band combined with a band gap (2.7 eV). This review summarised recent works in the development of titania incorporated with graphitic carbon nitride (g-C₃N₄) for enhanced photocatalytic activity.

Keywords: Photocatalyst; titanium dioxide; graphitic carbon nitride; heterojunction; visible light.

1.0 INTRODUCTION

Recently, the industrial development has caused a major threat towards aquatic life and the environment. This is due to industrial wastewater production such as from pesticides, heavy metals, dyes, pharmaceuticals, and personal care products, which are not simply biodegradable [1, 2]. The utilisation of polluted water resources that are toxic and carcinogenic often leads to human health problem and aquatic life threat [2]. Therefore, many researchers have created various methods to solve this problem by using conventional treatment processes such as adsorption, chemical, and biological treatment. However, some contaminants in wastewater are intractable to degrade by applying these conventional processes. Nowadays, advanced oxidation process (AOP) is the most promising technique and has been explored by researchers to degrade various types of pollutants [3].

The photocatalytic reaction using a heterogeneous catalyst, which is one of the AOPs, has emerged as a destructive method that can mineralise most organic pollutants [4]. The use of semiconductor materials for that purpose has gained attention by many researchers for removal of organic pollutants from an aqueous solution. Various semiconductors such as TiO₂, ZnO, Fe₂O₃, CdS, and ZnS can act as photocatalysts for light-induced redox process. Among them, titania (TiO₂) is the first semiconductor that was initially explored by Fujishima and Honda during photoelectrolysis of water to H₂ in 1972 [3]. TiO₂ has been studied extensively as a photocatalyst due to its inexpensive, chemically and photo-stable, non-toxic, and reusable. However, the fast electron-hole recombination and wide band gap of TiO₂ (~3.2 eV) limit its photoactivity and it is only applicable for ultraviolet (UV) irradiation [3-6]. Hence, many efforts have been devoted to extend the optical response of the

photocatalyst by incorporation of TiO_2 with $\text{g-C}_3\text{N}_4$. A short review on recent studies of $\text{TiO}_2/\text{g-C}_3\text{N}_4$ composite is covered in this paper.

2.0 TITANIUM DIOXIDE

Titanium dioxide (TiO_2) is present in three phases, which are anatase, rutile, and brookite. Anatase and rutile are formed in a tetragonal structure whereas brookite appears in an orthorhombic structure as shown in Figure 1 [7]. These phases are similar based on the octahedral structure with different assembly patterns of each octahedral chain. Among them, anatase TiO_2 is the most widely used in photocatalytic reaction and favoured for modification with other materials due to higher density of localised state that attributed towards slower charge carrier recombination [8, 9].




Figure 1. TiO_2 crystal structures [7].

Photocatalysis reaction conducted in visible light irradiation has become the main focus nowadays since it requires low energy for catalyst activation [10]. Even though TiO_2 is a promising photocatalyst, it is unable to absorb visible light due to its wide band gap energy, which limits its application range [6, 8, 10]. Hence, efforts have been devoted to prolong the optical response of TiO_2 from UV to the visible light region and various strategies have been explored including doping with metals or non-metals, dye or semiconductor sensitisation, and surface modification [11-13]. Nevertheless, it is a big challenge to obtain viable visible light active materials that are easily prepared, efficient, stable, and inexpensive.

3.0 GRAPHITIC CARBON NITRIDE ($\text{g-C}_3\text{N}_4$)

Polymeric $\text{g-C}_3\text{N}_4$ is depicted in Figure 2. Both triazine and heptazine have been discussed as possible tectonic units to constitute stable allotropes of $\text{g-C}_3\text{N}_4$. Based on density functional theory (DFT), the structure based on repeating heptazine units is more stable than the triazine units.




Figure 2. Representation of $\text{g-C}_3\text{N}_4$ based on a) triazine and b) heptazine units [14].

Particularly, $\text{g-C}_3\text{N}_4$ has become one of the most intensively researched photocatalytic materials due to its capability to be used in visible light radiance [15, 16]. Besides, $\text{g-C}_3\text{N}_4$ has high thermal stability, biocompatible, and resistant to oxidation and hydrolysis processes. The constricted band gap of $\text{g-C}_3\text{N}_4$ (~2.7 eV) enables it to penetrate visible light up to 460 nm [17].

However, g-C₃N₄ still consists of high recombination probability of photogenerated electron-hole charge carriers that limits photocatalytic efficiency.

4.0 TiO₂/g-C₃N₄ COMPOSITE

In improving photocatalytic activity, one of the strategies is to use a composite of two or more semiconductor photocatalysts that can absorb different parts of solar spectrum [18]. Composite semiconductors can also improve electron-hole separation due to the band off-sets and charge-transfer across interfaces. The coupling of carbon nitrides such as g-C₃N₄ with other semiconductor materials has gained interest of many researchers, for example the production of g-C₃N₄/TiO₂ and or TiO₂/g-C₃N₄ composites [19-21]. These composites show great improvement in the efficiencies of photoactivity, thus promote its applications in energy production and environmental remediation. Recent studies on this photocatalyst are shown in Table 1. The composite catalysts showed high photodegradation performance towards various pollutants under visible light, which are attributed by the optimum band gap factor and better electron-hole pair separation.

Table 1. Recent study on g-C₃N₄/ titania photocatalyst.

Photocatalyst	Synthesis Method	Pollutant	Band Gap (eV)	Performance	References
TiO ₂ /C ₃ N ₄ core-shell nanowire arrays	Hydrothermal	Bisphenol A	2.90	95%	[21]
Core-shell structure g-C ₃ N ₄ @TiO ₂	Sol-gel approach in-situ coating re-assembled	Phenol	1.70	30%	[22]
TiO ₂ /g-C ₃ N ₄ hollow nanotube	Molten salts	Rhodamine B	2.48	95%	[23]
TiO ₂ /g-C ₃ N ₄ mesostructured nanosheets	Facile calcination-sonication assisted method	Phenol	2.31	93%	[24]
Core-shell TiO ₂ @g-C ₃ N ₄ hollow microspheres	Two-step self-assembly procedure with the assistance of ultrasonic dispersion	Rhodamine B	2.75	93%	[25]
Porous g-C ₃ N ₄ /TiO ₂ heterostructure	In-situ assembling of small needle-like TiO ₂ on the surface of ultrathin g-C ₃ N ₄ sheets	Acid Orange	2.90	82%	[26]
Mesoporous TiO ₂ /g-C ₃ N ₄ microspheres	Facile nanocoating	Phenol	1.50	25%	[27]
Brookite/anatase TiO ₂ /g-C ₃ N ₄ heterojunction	Facile nanocoating	Phenol	1.80	20%	[28]
Carbon nitride/titania nanotubes	High-temperature calculation method	2-chlorophenol	2.60	90%	[29]

5.0 MECHANISM OF TiO₂/g-C₃N₄ COMPOSITE

Most of the TiO₂/g-C₃N₄ composites show a similar proposed mechanism. When TiO₂/g-C₃N₄ is exposed to visible light, the photon could be absorbed directly by g-C₃N₄ to generate the electron-hole pairs in valence band (VB) and conduction band (CB), respectively [30]. The electron from g-C₃N₄ can easily migrate from its CB to the CB of TiO₂ since g-C₃N₄ has more negative CB level (-1.12 eV) than TiO₂ (-0.29 eV) [31]. Meanwhile, the holes from TiO₂ surface will migrate to the VB of g-C₃N₄. The electron on CB of TiO₂ can abduct O₂ to generate superoxide anion radical ($\bullet\text{O}_2^-$), which is one of the active species that can oxidise the pollutant. Meanwhile, the holes on g-C₃N₄ also play an important role in photodegradation process by forming hydroxyl radical ($\bullet\text{OH}$) when reacted with water. The pollutant will be decomposed to form CO₂ and H₂O via photocatalysis with the reactive $\bullet\text{O}_2^-$ and $\bullet\text{OH}$ as illustrated in Figure 3.




Figure 3. Mechanism for photo-degradation of TiO₂/g-C₃N₄ composite [30].

6.0 CONCLUSION

From this review, it can be concluded that the coupling of these two semiconductors will increase the efficiency of electron transfer separation process. Consequently, the electron life is significantly prolonged and recombination process can be reduced, thus resulting in remarkable photocatalytic degradation of pollutants.

Acknowledgements

This research work was sponsored and supported by Universiti Teknologi Malaysia through Research University Grant No. 19H04.

References

- [1] Mohamed, N. B., and S. A. Raed. 2015. Review Article: Chemical Oxidation and Membrane Filtration Technologies for Wastewater Treatment. *Australian Journal of Basic and Applied Sciences*. 9: 263-273.
- [2] Azami, M. S., W. I. Nawawi, Ali H. Jawad, M. A. M. Ishak, K. Ismail. 2017. N-doped TiO₂ Synthesised via Microwave Induced Photocatalytic on RR4 Dye Removal under LED Light Irradiation. *Sains Malaysiana* 46: 1309-1316.
- [3] Fujishima, A., and K. Honda. 1972. Electrochemical Photolysis of Water at a Semiconductor Electrode. *Nature*. 238: 37-38.
- [4] Nawawi, W. I., M. S. Azami, L. S. Ang, M. A. M. Ishak, K. Ismail. 2017. Modification and Characterization of Microwave Assisted N doped TiO₂ – A Photodegradation Study under Suspension and Immobilized System. *Water Quality Research Journal of Canada*. 51-63.
- [5] Jaafar, N. F., A. A. Jalil, S. Triwahyono. 2017. Visible-Light Photoactivity of Plasmonic Silver Supported on Mesoporous TiO₂ Nanoparticles (Ag-MTN) for Enhanced Degradation of 2-chlorophenol: Limitation of Ag-Ti Interaction. *Applied Surface Science*. 392: 1068–1077.
- [6] Hitam, C. N. C., A.A. Jalil, S. Triwahyono, A.F.A. Rahman, N.S. Hassan, N.F. Khusnun, S.F. Jamian, C.R. Mamat, W. Nabgan, A. Ahmad. 2018. Effect of Carbon-Interaction on Structure-Photoactivity of Cu Doped Amorphous TiO₂ Catalysts for Visible-Light-Oriented Oxidative Desulphurization of Dibenzothiophene. *Fuel*. 216: 407-417.
- [7] Regonini, D., C. R. Bowen, A. Jaroenworoluck, R. Stevens. 2013. A Review of Growth Mechanism, Structure and Crystallinity of Anodized TiO₂ Nanotubes. *Materials Science and Engineering: R: Reports*. 74: 377-406.
- [8] Aziz, F. F. A., A. A. Jalil, S. Triwahyono, M. Mohamed. 2018. Controllable Structure of Fibrous SiO₂-ZSM-5 Support Decorated with TiO₂ Catalysts for Enhanced Photodegradation of Paracetamol. *Applied Surface Science*. 455: 84-95.
- [9] Valentin, C. D., and G. Pacchioni. 2013. Trends in Non-Metal Doping of Anatase TiO₂: B, C, N and F. *Catalysis Today*. 206:12–18.
- [10] Azami, M. S., S. K. Ain, R. Zaharudin, F. Bakar, W. I. Nawawi. 2016. Nitrogen Doped TiO₂ Prepared under Microwave Irradiation: Effect of Different Irradiation Light. *Applied Mechanics and Materials*. 835: 372-377.
- [11] Pan, L., G. Shen, J. Zhang, X. Wei, L. Wang, J. Zou, X. Zhang. 2015. TiO₂-ZnO Composite Sphere Decorated with ZnO Clusters for Effective Charge Isolation in Photocatalysis. *Industrial & Engineering Chemistry Research*. 54: 7226–7232.

- [12] Azami, M. S., W. I. Nawawi, D. S. M. Shukri. 2017. Formation of Predominant Interstitial N–TiO₂ using Physical Preparation under Microwave Irradiation for Reactive Red 4 Dye Removal. *Desalination and Water Treatment*. 92: 172-180.
- [13] Jaafar, N. F., A. A. Jalil, S. Triwahyono, J. Efendi, R. R. Mukti, R. Jusoh, N. W. C. Jusoh, A. H. Karim, N. F. M. Salleh, V. Suendo. 2015. Direct in Situ Activation of Ag⁰ Nanoparticles in Synthesis of Ag/TiO₂ and its Photoactivity. *Applied Surface Science*. 338: 75–84.
- [14] Li, J., Y. Liu, H. Li, C. Chen J. 2016. Fabrication of g-C₃N₄/TiO₂ Composite Photocatalyst with Extended Absorption Wavelength Range and Enhanced Photocatalytic Performance. *Journal of Photochemistry and Photobiology A: Chemistry*. 317: 151-160.
- [15] Yasuhiro, S. K., Yusuke, S. Hirokatsu, T. Shunsuke, I. Satoshi, H. Takayuki. 2015. Effects of Surface Defects on Photocatalytic H₂O₂ Production by Mesoporous Graphitic Carbon Nitride under Visible Light Irradiation. *ACS Catalysis*. 5: 3058-3066.
- [16] Mohammad, R. G., B. Francois, D. Trong-On. 2016. Graphitic Carbon Nitride-Titanium Dioxide Nanocomposite for Photocatalytic Hydrogen Production under Visible Light. *International Journal of Chemical Reactor Engineering*. 14: 851-858.
- [17] Usanginee, N., M. Lagnamayee, P. Kulamani. 2015. Visible Light Driven Novel g-C₃N₄/NiFe-LDH Composite Photocatalyst with Enhanced Photocatalytic Activity towards Water Oxidation and Reduction Reaction. *Journal of Materials Chemistry A*. 3: 18622-18635.
- [18] Yanlong, T., C. Fuxing, Z. Xiang, Y. Fei, Z. Baocheng, C. Zhi, L. Jiyang, X. Fengna, D. Xiaoping. 2014. Solvothermal Synthesis and Enhanced Visible Light Photocatalytic Activity of Novel Graphitic Carbon Nitride–Bi₂MoO₆ Heterojunctions. *Powder Technology*. 267: 126-133.
- [19] He, Y., Y. Wang, L. Zhang, B. Teng. 2015. High-Efficiency Conversion of CO₂ to Fuel over ZnO/g-C₃N₄ Photocatalyst. *Applied Catalysis B: Environmental*. 168-169:1-8.
- [20] He, Y., L. Zhang, M. Fan, X. Wang, L. W. Mikel, Q. Nong, Y. Wu, L. Z. Zhao. 2015. Z-scheme SnO₂/g-C₃N₄ Composite as an Efficient Photocatalyst for Dye Degradation and Photocatalytic CO₂ Reduction. *Solar Energy Materials and Solar Cells*. 137: 175-184.
- [21] Wang, Y., Q. Wu, Y. Li, L. Liu, Z. Geng, Y. Li, J. Chen, W. Bai. 2018. Controlled Fabrication of TiO₂/C₃N₄ core-shell Nanowire Arrays: a Visible-Light-Responsive and Environmental Friendly Electrode for Photoelectrocatalytic Degradation of Bisphenol A. *Journal of Materials Science: Materials in Electronics*. 53: 11015-11026.
- [22] Wang, Y., W. Yang, X. Chen, J. Wang, Y. Zhu. 2018. Photocatalytic Activity Enhancement of Core-Shell Structure g-C₃N₄@TiO₂ via Controlled Ultrathin g-C₃N₄ Layer. *Applied Catalysis B: Environmental* 220: 337-347.
- [23] Yan, X., Q. Gao, J. Qin, X. Hui, Z. Ye, J. Li, Z. Ma. 2018. A Facile Method for Fabricating TiO₂/g-C₃N₄ Hollow Nanotube Heterojunction and its Visible Light Photocatalytic Performance. *Materials Letters*. 217: 1-4.
- [24] Tan, S., Z. Xing, J. Zhang, Z. Li, X. Wu, J. Cui, J. Kuang, Q. Zhu, W. Zhou. 2018. Ti³⁺-TiO₂/g-C₃N₄ Mesostructured Nanosheets Heterojunctions as Efficient Visible-Light-Driven Photocatalysts. *Journal of Catalysis*. 357: 90-99.
- [25] Ma, L., G. Wang, C. Jiang, H. Bao, Q. Xua. Synthesis of Core-Shell TiO₂@g-C₃N₄ Hollow Microspheres for Efficient Photocatalytic Degradation of Rhodamine B under Visible Light. *Applied Surface Science*. 430: 263-272.
- [26] Li, Y. N., Z. Y. Chen, M. Q. Wang, L. Z. Zhang, S. J. Bao. 2018. Interface Engineered Construction of Porous g-C₃N₄/TiO₂ Heterostructure for Enhanced Photocatalysis of Organic Pollutants. *Applied Surface Science*. 440: 229-236.
- [27] Wei, H., W. A. McMaster, J. Z. Y. Tan, L. Cao, D. Chen, R. A. Caruso. 2017. Mesoporous TiO₂/g-C₃N₄ Microspheres with Enhanced Visible-Light Photocatalytic Activity. *Journal of Physical Chemistry C*. 121: 22114-22122.
- [28] Wei, H., W. A. McMaster, J. Z. Y. Tan, L. Cao, D. Chen, R. A. Caruso. 2018. Tricomponent Brookite/Anatase TiO₂/g-C₃N₄ Heterojunction in Mesoporous Hollow Microspheres for Enhanced Visible-Light Photocatalysis. *Journal of Materials Chemistry A*. 6: 7236-724.
- [29] Anjum, M., R. Kumar, S. M. Abdelbasir, M. A. Barakat. 2018. Carbon Nitride/Titania Nanotubes Composite for Photocatalytic Degradation of Organics in Water and Sludge: Pre-Treatment of Sludge, Anaerobic Digestion and Biogas Production. *Journal of Environmental Management*. 223: 495–502.
- [30] Zhang, J. J., S. S. Fang, J. Y. Mei, G. P. Zheng, X. C. Zheng, X. X. Guan. 2018. High-Efficiency Removal of Rhodamine B Dye in Water using g-C₃N₄ and TiO₂ co-Hybridized 3D Graphene Aerogel Composites. *Separation and Purification Technology*. 194: 96–103.
- [31] Boonprakob, N., N. Wetchakun, S. Phanichphant, D. Waxler, P. Sherrell, A. Nattestad, J. Chen, B. Inceesungvorn. 2014. Enhanced visible-light photocatalytic activity of g-C₃N₄/TiO₂ films. *Journal of Colloid and Interface Science*. 417: 402-409.